

## HIGHTEC GREASEGUARD EP 2

Premium, multi-purpose lubricating grease based on lithium soap with pronounced EP (Extreme Pressure) properties for use in rolling and sliding bearings.

### Description

HIGHTEC GREASEGUARD EP 2 is a multi-purpose grease produced using selected base oils and lithium-based thickeners with chemically-acting EP additives.

### Application

HIGHTEC GREASEGUARD EP 2 is used as a multi-purpose grease for lubricating rolling and sliding bearings subjected to high pressure loads. It is particularly suitable for the multi-functional lubrication of power-driven vehicles as well as industrial and construction machinery.

### The quality of this product is equivalent to EU regulations

- DIN 51 502/51 825: KP 2 K-30
- T[°C]: -30 ... +120
- T[°F]: -22 ... +248

### Benefits

- First-class economy grade for multi-functional use in rolling and sliding bearings
- Very good wear protection properties
- Very good stability
- Outstanding resistance to oxidation
- Excellent pressure absorption capacity
- Good corrosion protection
- Very good resistance to water
- Good adhesive power

### Notices

If stored appropriately in originally sealed containers in a dry place, away from direct sunlight and at temperatures between 10°C and 30°C, the minimum storage period is 24 months.

A safety data sheet is available upon request for information on health, safety and environmental aspects. A little oil separation is caused by the product's attributes and harmless.

It is desirable to a certain extent to ensure lubrication, and no indication of inferior product quality. The separated oil can be incorporated again homogeneously by folding it in comprehensively.

### Typical characteristics

Property	Method	Unit	Value
Classification	DIN 51 502	-	KP 2 K-30
	ISO 6743-9	-	ISO-L-X-CCEB2
NLGI-class	DIN 51 818	-	2
Thickener type	-	-	Lithium
Color	visuell	-	braun / brown
Base oil viscosity at 40 ° C	ASTM D-7042	mm²/s	130
Worked penetration	DIN ISO 2137	0,1 mm	265 - 295
Dropping point	DIN ISO 2176	°C	> 185
VKA welding force	DIN 51 350-4	N	3000
Corrosion protection (Emcor)	DIN 51 802	Korr.-Grad	0-0
Corrosion effect on copper	DIN 51 811	Korr.-Grad	1-100
Resistance to water	DIN 51 807-1	Bew.-Stufe	1-90
Usage temperature	-	°C	-30 bis +120
Usage temperature	-	°F	-22 bis +248
	-	-	Mineralisch / mineral based

The characteristics shown are typical of current production. This data cannot be constructed as a legally binding warranty or guaranty of certain product properties or of the suitability of the product for a specific application. ROWE products are continually improved. Therefore ROWE reserves the right to change all the technical data in this product information at any time without notice. All sales and deliveries shall be subject to our current General Terms and Conditions of Sale and Terms ([www.rowe-oil.com](http://www.rowe-oil.com)).

